

Chemicals contained in products

Package-type

Epson Package name; **PFBGA12U-180 / Halogen free**

JEITA Package name; **(P-TFBGA-180-1212-0.80)**

Solder ball Type; **Lead(Pb) Free**

Weight; **0.28 [g] *Note1**

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content ※2		Application		
					[mg]	[ppm]			
IC Die	IC Die	18.3	Silicon	7440-21-3	18.3	999894	Base material		
			Boron	7440-42-8	0.00004	2	Dopant		
			Phosphorus	7723-14-0	0.00009	5	Dopant		
			Aluminum	7429-90-5	0.0004	20	Metalization		
			Arsenic *Note3	7440-38-2	0.00009	5	Dopant		
			Fluorine *Note3	7782-41-4	0.00004	2	Dopant		
			Titanium *Note3	7440-32-6	0.0004	20	Metalization		
			Molybdenum *Note3	7439-98-7	0.0004	20	Metalization		
			Tungsten *Note3	7440-33-7	0.0005	30	Metalization		
			Cobalt *Note3	7440-48-4	0.00004	2	Metalization		
	Stress buffer coat	0.37	Polyimide	-	0.37	1000000	Stress buffer coat *Note4		
Package	Substrate	60.7	Glass-cloth	-	8.00	132000	Reinforcement		
			Silica	-	4.00	66000	Filler		
			Epoxy resin	-	9.90	164300	Base material		
			Acrylate resin	-	5.20	85000	Base material		
			Pigment	-	3.00	49300	Additive		
			Organic filler	-	0.21	3400	Filler		
			Arsenic	7440-38-2	0.005	85	Burning resistance		
			Chromium compound	-	0.0009	15	Burning resistance		
			Copper	7440-50-8	25.5000	419900	Copper foil		
			Nickel	7440-02-0	3.9	64000	Plating		
			Gold	7440-57-5	0.99	16000	Plating		
			Die Bonding material	4.30	Epoxy resin	-	2.900	670000	Adhesive
					Acrylic resin	-	1.40	330000	Adhesive
	Solder ball	36.6	Tin	7440-31-5	35.10	957500	Solder ball		
			Silver	7440-22-4	1.3	35000	Solder ball		
			Copper	7440-50-8	0.27	7500	Solder ball		
	Bonding Wire	3.5	Gold	7440-57-5	3.500	1000000	Conductor		
	Mold resin	156.20	Epoxy resin	-	7.80	50000	Base material		
			Silica	60676-86-0/-	136.3	873000	Filler		
			Carbon black	1333-86-4	0.310	2000	Coloring agent		
			Hardening chemical(ex:Phenol resin)	-	7.80	50000	Base material		
			Organic phosphorous compound	-	0.8	5000	Hardening accelerator		
			others	-	3.1	20000	Additive		

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

*Note4 The stress buffer coat may not be used depending on the individual model.